



PATENT ABSTRACTS OF JAPAN

(11) Publication number: **11031416 A**(43) Date of publication of application: **02 . 02 . 99**

(51) Int. Cl

H01B 1/20
G03F 7/004
G03F 7/004
G03F 7/027
G03F 7/028
G03F 7/038
H01B 1/22
H01L 23/12
H05K 1/09

(21) Application number: **10163173**(22) Date of filing: **11 . 06 . 98**(30) Priority: **24 . 01 . 92 JP 04 11146**(62) Division of application: **05009270**(71) Applicant: **TORAY IND INC**

(72) Inventor: **MASAKI YOSHIKI**
YOSHIMURA AKIKO
NOMURA HIDESHI

(54) PHOTSENSITIVE CONDUCTIVE PASTE**(57) Abstract:**

PROBLEM TO BE SOLVED: To form a fine and low-resistant circuit pattern by including one or more kinds of conductive powder selected from group of Au, Ag, Pd and Pt, an acrylic group copolymer having an acid value in a specified range, a photo-reactive compound and a photo-polymerization initiator.

SOLUTION: A predetermined quantity of one to three kinds of conductive powder selected from Au, Ag, Pd and Pt, an acrylic group copolymer having an acid value at 40-200, a photo-reactive compound and glass flit are prepared. The predetermined quantity of a metal oxide

and a photo-polymerization initiator are added to the described material, and they are mixed and dispersed so as to obtain the paste, and this paste is set-solid on an alumina board, to which a surface treatment is performed, for printing, and thereafter dried. Exposure is performed by using a chrome mask formed with a fine pattern, and development and washing are performed, and thereafter, it is burned at 500°C, and sintered at 800-1000°C. A fine and a low-resistant circuit pattern, which has a film thickness at 12-20 μm, a resolution at 10-60 μm and a specific resistance at 3-18 μΩ.cm, is thereby obtained.

COPYRIGHT: (C)1999,JPO